

Packline

<i>Substance</i>	<i>Caliper</i>	<i>Bursting</i>	<i>Stiffness</i>	
<i>g/m²</i>	<i>mm</i>	<i>strength</i>	<i>Resonance</i>	<i>method</i>
			<i>md</i>	<i>cd</i>
unlined / unlined				
400,00	0,54	450	45	20
450,00	0,69	475	65	35
500,00	0,77	500	85	45
550,00	0,85	525	110	60
600,00	0,92	550	140	80
650,00	1,00	575	175	100
700,00	1,08	600	210	125
750,00	1,15	625	255	150
800,00	1,23	650	305	180
850,00	1,31	675	360	215
900,00	1,39	700	420	255
white kraft / unlined				
600,00	0,83			
700,00	1,02			
800,00	1,13	875	430	205
Unlined / white kraft				
700,00	1,02			
Brown kraft / unlined				
600,00	0,87			
750,00	1,05	850	360	175
850,00	1,21	900	505	245
White kraft / white kraft				
550,00	0,77			
600,00	0,83	875	210	105
700,00	0,98	925	320	165
750,00	1,05	950	385	200
800,00	1,12	975	460	240
850,00	1,19			
900,00	1,26	1025	630	330
White kraftliner / white testliner				
1.000,00	1,40			
White testliner / white kraftliner				
1.000,00	1,40			
White kraftliner / white kraftliner				
1.050,00	1,47			
1.100,00	1,54			

White kraft / brown kraft

600,00	0,83	875	210	105
650,00	0,91			
700,00	0,98	925	320	165
750,00	1,05	950	385	200
800,00	1,13	975	460	240
850,00	1,19			
900,00	1,28	1025	630	330

White kraft / TK liner

750,00	1,05			
800,00	1,14	1000	460	220
850,00	1,19			
900,00	1,26	1050	610	270
950,00	1,33			
1.000,00	1,40	1100	770	390
1.050,00	1,47			
1.100,00	1,54	1150	950	480

White testliner / TK liner

1.050,00	1,47
1.100,00	1,54
1.150,00	1,61
1.200,00	1,68
1.250,00	1,75

White kraftliner / kraftliner

1.100,00	1,54
1.200,00	1,68
1.250,00	1,75

White kraftliner / TK liner

1.100,00	1,54
1.200,00	1,68
1.250,00	1,75

Brown kraft / white kraft

600,00	0,83	875	210	105
650,00	0,91			
700,00	0,98	925	320	165
750,00	1,05	950	385	200
800,00	1,13	975	460	240
850,00	1,19			
900,00	1,28	1025	630	330

TK liner / white kraft

750,00	1,05			
800,00	1,14	1000	460	220
850,00	1,19			
900,00	1,28	1050	610	270
950,00	1,33			
1.000,00	1,43	1100	770	390
1.050,00	1,47			
1.100,00	1,58	1150	950	480

TK liner / white testliner

1.050,00	1,47
1.100,00	1,58

TK liner / white kraftliner

1.100,00	1,58
1.250,00	1,75

Brown kraft / brown kraft

500,00	0,67			
550,00	0,77			
600,00	0,83	975	265	120
650,00	0,90	1000	335	150
700,00	0,97	1025	415	185
750,00	1,05	1050	495	225
800,00	1,13	1075	580	270
850,00	1,20	1100	665	320
900,00	1,27	1125	750	375
1.000,00	1,42	1175	920	500

Brown kraft / TK liner

1.000,00	1,40
----------	------

TK liner / TK liner

800,00	1,13			
850,00	1,20			
900,00	1,26	1150	660	290
950,00	1,33	1200	805	335
1.000,00	1,40	1225	945	385
1.050,00	1,47	1275	1085	445
1.100,00	1,54	1300	1235	510
1.150,00	1,61	1350	1390	590
1.200,00	1,68	1375	1550	675
1.250,00	1,75	1425	1710	780
1.300,00	1,82	1475	1990	875
1.350,00	1,93			

Kraftliner / kraftliner

900,00	1,26	1700	975	420
1.100,00	1,54	2100	1335	605
1.250,00	1,75	2400	2130	935
1.300,00	1,82	2500	2355	1035
1.400,00	2,00	2600	2770	1160
1.600,00	2,26	3100	3900	1995

Ribbed kraft / ribbed kraft

600,00	0,83	975	265	120
650,00	0,90	1000	335	150
750,00	1,05	1050	495	225
850,00	1,20	1100	665	320

<i>Packline</i>	<i>Specifications</i>	<i>Units</i>	<i>Tolerances</i>	<i>Test methods</i>
Caliper	see matrix	mm	±7%	ISO 534
Substance	see matrix	g/m ²	±3 %	ISO 536
Stiffness	see matrix	mNm	±15 %	ISO 5629
Bursting strength	see matrix	kPa	±20 %	ISO 2759
Flatness	0	%	-0,3/+1,5 %	SKSB
Flatness (pe lined)	0	%	-0,3/+2,5 %	SKSB
Moisture content	9,0	%	±1,0 %	ISO 287
Pick up	Substance < 1050 g/m ²	%	< 10	ASCO 1969
Pick up	1050 < Substance < 1250 g/m ²	%	< 15	ASCO 1969
Pick up	Substance > 1250 g/m ²	%	< 20	ASCO 1969