

## 5) DISPLAYLINE

Indication of technical data				
Product	Caliper fix (mm)	Thickness ca. (g/m <sup>2</sup> )	Stiffness MR dynamic ISO 5628 (mNm)	Stiffness DR dynamic ISO 5628 (mNm)
5.c Print / Print (FSC® mix 70% CU-COC-810587)	0,80	625	240	135
	1,00	775	445	270
5.e Premium Print (FSC® mix 70% CU-COC-810587)	1,25	830	In development	In development
	1,60	1.040	In development	In development
	1,80	1.170	In development	In development
	1,90	1.240	In development	In development
Moisture (ABS) (%)		8,00%		
Tolerance Moisture (%)		+/- 1		
Tolerance Thickness (%)		+/- 3		
Plybond DIN 54516 (N/min)		40		
Machine width (cm)		215 - 230 cm (200-214 for PRINT 2,25/3,0)* <sup>1</sup>		
Product (all weather board)	Substance fix (g/m <sup>2</sup> )	Thickness approx. (mm)	Stiffness MR dynamic ISO 5628 (mNm)	Stiffness DR dynamic ISO 5628 (mNm)
5.g White Kraftliner + White PE / Kraftliner + PE	1000	1,39	990	420
Moisture (%)		9,00		
Tolerance Moisture (%)		+/- 1		
Tolerance Thickness (%)		+/- 3		
Plybond DIN 54516 (N/min)		40		
FSC Certificate (Claim)		FSC® mix 70% CU-COC-810587		
Machine width (cm)		215 - 230 cm		
* <sup>2</sup> On request				02-2019